



PRECISION TESTING LABORATORIES, INC.

313 Hill Avenue, NASHVILLE TN 37210-4711
 PHONE 615-254-3401 FAX 615-254-3488
www.precisiontesting.com

Laboratory Report No. 14001
 30-Oct-12

Page 1 of 2

Mr. Bob Wright
 Floor Signage, LLC
 7099 Huntley Rd.
 Columbus, OH 43229

PO#: n/a
Item: One (1) floor tile sample (qty. 4 tiles)
Identification: Sample ID: DURAMarker GRIP - White non-skid
Purpose: Slip Resistance, ASTM F 1677-05
 Rubber Property, Durometer Hardness, ASTM D 2240-05

Test	Unit of Measure	Specimen Results				Average	Stdev
<u>Slip Resistance</u>							
<u>ASTM F 1677-05, Mark II</u>							
<u>Neolite Finline - J & M</u>							
Heel							
		<u>A</u>	<u>B</u>	<u>C</u>	<u>D</u>		
	<u>Tile # 1</u>						
	Dry	0.59	0.59	0.58	0.59	0.59	0.01
	Wet	0.52	0.52	0.51	0.52	0.52	0.01
	<u>Tile # 2</u>						
	Dry	0.60	0.61	0.60	0.60	0.60	0.01
	Wet	0.53	0.52	0.52	0.51	0.52	0.01
	<u>Tile # 3</u>						
	Dry	0.60	0.60	0.60	0.61	0.60	0.01
	Wet	0.52	0.52	0.51	0.52	0.52	0.01
					<u>Dry Average (3 tiles)</u>	0.60	n/a
					<u>Wet Average (3 tiles)</u>	0.52	n/a
<u>Slip Resistance, Test Description</u>							
Dry =	Dry						
Wet =	25 mls distilled water						
Greasy =	3.0 grams Crisco brand shortening applied until just opaque						
Greasy/Wet =	25 mls of distilled water w/ 3.0 grams Crisco brand shortening applied until just opaque						

Rubber Property, Durometer Hardness

ASTM D 2240-05


Shore Instrument Durometer Type A


as received

Neolite Finline - J & M	90	92	90	89	90	90	1
-------------------------	----	----	----	----	----	----	---

A Shore Instrument Durometer Type "A", serial # 88533, utilizing a Shore Type 1 operating stand with a constant contact pressure of 865 grams was used for the test sequence. All readings are taken at a 1 second timed interval after specimen contact in a controlled atmosphere of 72° F and 50% RH. Meter calibrations are conducted prior to test.

I certify that the above tests under my supervision were performed in accordance with the specification test requirements and that the reported results are true, valid and applicable to the samples tested. I further certify that these samples were the only samples tested from the lot of end items identified above.

Signed: 
Suzanne Piispanen, VP Operations

Signed: 
Don G. Roney, Laboratory Manager

This report is limited to and related only to the particular instrument, material or other subject to which it refers. These test results can not be compared to results obtained using different methods or under different conditions. No representation is made that similar articles will be of like quality. Neither Precision Testing Laboratories, Inc (hereinafter "Precision Testing") nor their officers, directors, managers or employees, shall be responsible for any loss or damage resulting directly or indirectly from any failure, error or omission in testing, or in the reporting of test results. Precision Testing has no controls, and assumes no responsibility for the tested product's functionality or use. Precision Testing's liability shall not exceed the fees paid for the testing reflected on this report. Precision Testing observes and maintains client confidentiality, and limits reproduction of this report, except in full, without prior approval of Precision Testing.

tj(gm)